

## A2243 – Technical Data Sheet



Bondrite Adhesives Limited  
Unit 3H  
Sibley Road Industrial Estate  
Barrow-Upon-Soar  
Leicestershire LE12 8LP  
Tel: 01509 815550

### Description

**A2243** is designed for the sealing and locking of threaded fasteners which may require easy disassembly with standard hand tools. The product is a single component anaerobic, medium strength thixotropic, acrylic based threadlocker. The product cures when confined in the absence of air between close fitting metal surfaces and prevents leakage and loosening from vibration and shock.

**A2243** is particularly suitable for uses on less active substrates such as plated surfaces and stainless steel, where disassembly is required with hand tools.

### Characteristics

<b>Base</b>	Dimethacrylate ester
<b>Fluorescence</b>	Positive under UV
<b>Viscosity</b>	1200-3000 cps
<b>Fixture Time</b>	10 to 15 mins
<b>Colour</b>	Blue
<b>Specific Gravity (25°C)</b>	1.08
<b>Flash point</b>	See MSDS
<b>Cure</b>	Anaerobic

### Typical Performance of Cured Material

	Typical value
<b>Operating temperature (After 24hr at 20-25°C on M10 steel nuts and bolts)</b>	-54°C to 150°C
<b>Breakaway torque M10 steel bolts and nuts ISO 10964</b>	20 Nm
<b>Prevail torque M10 steel bolts and nuts ISO 10964</b>	7 Nm

### Chemical / Solvent Resistance

Aged under conditions indicated and tested @ 22°C.

Environment	Temp °C	% of initial strength			
		100 h	500 h	1000 h	5000 h
<b>Motor oil (MIL-L-46152)</b>	<b>125</b>	<b>95</b>	<b>95</b>	<b>95</b>	<b>95</b>
<b>Leaded Petrol</b>	<b>22</b>	<b>100</b>	<b>100</b>	<b>95</b>	<b>95</b>
<b>Brake Fluid</b>	<b>22</b>	<b>100</b>	<b>100</b>	<b>100</b>	<b>100</b>
<b>Water/Glycol 50/50</b>	<b>87</b>	<b>95</b>	<b>80</b>	<b>80</b>	<b>80</b>
<b>Acetone</b>	<b>22</b>	<b>100</b>	<b>100</b>	<b>85</b>	<b>85</b>
<b>Ethanol</b>	<b>22</b>	<b>100</b>	<b>85</b>	<b>85</b>	<b>85</b>

## **Directions for use**

1. For optimum performance surfaces should be clean and free of grease (internal and external).
2. If the material is an inactive metal consider using activator.
3. Shake the product thoroughly before use.
4. Apply several drops to the bolt and nut.
5. Assemble and tighten as required.
6. To prevent the clogging of the nozzle, do not let the tip touch metal surface during application.

## **Disassembly**

1. Remove with standard hand tools.
2. In circumstances where hand tools do not work, use localized heat to bolt or nut, disassemble while hot.

## **Cleaning**

To remove cured product use a combination of solvent and abrasion such as a wire brush.

## **Precaution**

1. Use with proper ventilation. Avoid contact with skin and eyes.
2. If contact with skin occurs, rinse with warm water or dissolve gradually with appropriate debonder.
3. Do not try to remove forcibly.
4. If adhesive gets into eye, keep eye open and rinse thoroughly. Seek medical attention immediately.
5. Keep well out of reach of children.
6. This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be use with chlorine or other strong oxidising materials.
7. Where washing systems are used to clean the surfaces before bonding, it is important to check the compatibility of the washing solution with the adhesive. In some cases these solutions can affect the cure and performance of the adhesive.
8. This product is not recommended for use on certain plastics.

## **Please consult the A2243 Health & Safety Data Sheet for statutory regulation information.**

Information relating to the products of Bondrite Adhesive Limited is based on tests carried out under laboratory conditions. If any of our products are not used in accordance with our instructions or are used under conditions which vary from our laboratory, they may not perform in accordance with any information provided and Bondrite shall not have any liability in this case. Bondrite will accordingly provide samples of our products, on request and free of charge, for Customers to carry out their own tests as to suitability of our product for their purposes and as used in their intended environment.

Purchase from Bondrite