

## C2626 – Technical Data Sheet



Bondrite Adhesives Limited  
Unit 3H  
Sibley Road Industrial Estate  
Barrow-Upon-Soar  
Leicestershire LE12 8LP  
Tel: 01509 815550

### Description

**C2626** is a single-component brushable contact adhesive suitable for a range of internal and external applications. It is used extensively by both the professional and DIY hobbyist for general purposes, including shop fitting, kitchen fitting and general repairs.

It offers the following benefits:

- **C2626** is extremely versatile. It is ideal for bonding decorative laminates to wood composites due to its excellent heat-resistant adhesion properties. It will bond all grades of timber and most plastics. **C2626** is also suitable for use with hard furnishings, cotton-backed vinyl and most metals.
- The high initial bond-strength of **C2626** allows the immediate handling of joined substrates, whilst its long open tack-time of up to 20 minutes gives the flexibility you need to allow for unforeseeable delays. This makes **C2626** perfect for manual applications.
- There is no need for expensive specialist equipment to apply **C2626**. It is quickly and easily applied with a brush. This helps to minimise costs. **C2626** also has a high viscosity, which ensures a mess-free/waste-free/non-drip application.

### Physical Properties

Base	Polychloroprene
Appearance	Neutral
Application Temp.	5-30°C
Temperature Resistance	-30 to 90°C
Coverage	3-4m <sup>2</sup> / litre
Tack-Life (20°C)	5-20 minutes
Viscosity	6000cps
Storage	5-25°C
Environmental	See MSDS

### Directions for Use

Ensure surfaces to be bonded are clean and free from grease and other contaminants.

1. Condition materials to be bonded in the bonding environment overnight.
2. Stir **C2626** before use.
3. Apply a thin, even coat of adhesive to the surfaces of both substrates using a short stiff brush.
4. Align the panel edges and bond under maximum pressure as soon as the surfaces become 'touch dry' (adhesive is glossy and no longer transfers to the knuckles).
5. Laminates should be nip-rolled or platen-pressed for best results. If this is not possible, use a hard roller and go over the entire working surface with as much bodyweight as possible. Seams and edges should always receive extra pressure. If possible, sandwich the panel edge between wooden battens and use G-clamps.

**Please consult the C2626 Health & Safety Data Sheet for statutory regulation information.**

Information relating to the products of Bondrite Adhesive Limited is based on tests carried out under laboratory conditions. If any of our products are not used in accordance with our instructions or are used under conditions which vary from our laboratory, they may not perform in accordance with any information provided and Bondrite shall not have any liability in this case. Bondrite will accordingly provide samples of our products, on request and free of charge, for Customers to carry out their own tests as to suitability of our product for their purposes and as used in their intended environment.

**Purchase from Bondrite**

**Issue Date – November 2021**